



NASA OUTGASSING APPROVED PRODUCTS ASTM E595

FEATURED PRODUCTS

Application	Product	TML%	CVCM%	WVR	NML%
Potting (Thermally conductive, Dielectric)	RF 2022 (mod 1) + RF 619	0.43	<0.01	0.42	0.01
	RF 4407 + RF81	1.27	0.01	0.36	0.91
	RF 4407 + RF612	0.98	<0.01	0.43	0.55
	RF 5407 + RF24	0.30	0.00	0.14	0.16
Structural Pastes	RF 5004	1.51	<0.01	0.68	0.83
	RF 5063	1.49	<0.01	0.58	0.91
	RF 6110	0.74	0.02	0.69	0.05
Adhesives (Electrically conductive)	RF 713	0.82	<0.01	0.20	0.62
	RF 1029/971 (mod 2)	1.08	<0.01	0.70	0.38
	RF 1029/971	1.72	<0.01	0.99	0.73
	RF 2869 (mod 2)	0.44	<0.01	0.05	0.39
	RF 2969 (mod 2)	0.44	<0.01	0.05	0.39
	RF 2969 (mod 4)	0.21	<0.01	0.05	0.16
	RF 2969 (mod 7)	.553	.019		.534
Syntactics	RF 1131	1.99	0.07	0.31	1.68
	RF 1133	1.87	0.12	0.35	1.45
	RF 1135	0.69	<0.01	0.28	0.41
	RF 1141	0.67	<0.01	0.14	0.53
	RF 1143	0.87	<0.01	0.21	0.66
	RF 1163	0.85	0.13	0.16	0.69
	RF 1164	0.93	0.01	0.00	0.93