

18027 Bishop Avenue  
Carson, CA 90746-4019  
Phone: (800) 374-3872  
Fax: (310) 202-7247  
[www.evrobotics.com](http://www.evrobotics.com)



**Resin Formulators  
Technical Data Sheet  
RFC 2296 A/B  
MODIFIED SILICONE RTV**

## Description

RFC 2296 is a two part silicone RTV that has been modified to reduce density.

## Handling Properties, Typical

Property	RFC 2296 A/B
Mix Ratio: by Weight	100:0.6
by Volume	N/A
Mixed Color	White
Mixed Viscosity @ 77°F (25°C), cps	NT
Pot Life, 100 grams @ 77°F (25°C)	120 min
Cure Schedule	24 hr @ 77°F (25°C)

## Physical Properties, Typical Cured Performance

** Property	Test Method	Unit	Value
Shore hardness		A	40
Density		Lb/gal	9.2

\*\* Cure: 24 hr @ 25°C

**SAFETY INFORMATION:** See Materials Safety Data Sheet for RFC 2296 A & B for proper storage and handling.

### Notice to Buyer: Exclusion of Warranties and Limitation of Liability

This data sheet does not constitute a specification. All information supplied by Resin Formulators and E.V. Roberts is considered accurate, but is furnished upon the express condition that the person receiving it shall make their own tests to determine its suitability for their particular purpose.

Revised: DSoden 07-31-2013