

18027 Bishop Avenue
Carson, CA 90746-4019
Phone: (800) 374-3872
Fax: (310) 202-7247
www.evroberts.com



TECHNICAL DATA SHEET
RF 5000
LIQUID EPOXY RESIN

Description

Standard viscosity Bisphenol A epoxy.

Handling Properties, Typical

Property	RF 5000
Epoxide Equivalent Weight	182-192
Color (Gardener)	1 max
Viscosity @ 77°F (25°C), cps	11,000-15,000
Density	1.16

SAFETY INFORMATION: See Materials Safety Data Sheet for RF 5000 for proper storage and handling.

Notice to Buyer: Exclusion of Warranties and Limitation of Liability

This data sheet does not constitute a specification. All information supplied by Resin Formulators and E.V. Roberts is considered accurate, but is furnished upon the express condition that the person receiving it shall make their own tests to determine its suitability for their particular purpose. No warranty is expressed or implied regarding such information, the data upon which the same is based, or the results to be obtained from the use of such information or product will not infringe any patent.

Revised: D. Soden 07-15-2014